



Product information

GREY VACUUM FORMING SILICONE RUBBER SHEETING QUALITY: VB50



PROPERTY	VALUE
HARDNESS:	50° (+/-5°) Shore 'A'
TENSILE STRENGTH:	1300 psi
ELONGATION @ BREAK:	800%
MODULUS @ 300% ELONGATION:	400 psi
TEAR STRENGTH:	240 psi
COMPRESSION SET: (22hrs @ 350F)	19%

Issue 1

December 2005

Check out the download area of our website
www.j-flex.co.uk for other product information



Clockpress Limited
 Registered in England.
 Registration No. 2448048
 Registered Office:
 St Hugh's, 23 Newport,
 Lincoln LN1 3DN

J-FLEX RUBBER PRODUCTS

Engineering Rubber Components & Specialised Sheeting Products

Unit 1, London Road Business Park, Retford,
 Nottinghamshire, England DN22 6HG
 tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409
www.j-flex.co.uk

