



# Product information

## FDA COMPLIANT METAL DETECTABLE SILICONE MOULDED SHEET & EXTRUSION GRADE



PHYSICAL PROPERTIES	TYPICAL VALUES
COLOUR:	Blue
HARDNESS:	60° Shore 'A'
DENSITY:	1.27 gr/cm <sup>3</sup>
TENSILE STRENGTH:	7.0 N/mm <sup>2</sup>
ELONGATION @ BREAK:	400%
TEMPERATURE RANGE:	-60°C to 200°C Continuous

**Notes:** Metal detectable iron powder cut to 300 fine mesh in the ratio of 15 p.p.h. complete with silicone rubber binder.

The above typical values are obtained from moulded test pieces cured for 10 minutes @ 170°C and post cured for 4 hours @ 200°C.

The raw materials used to manufacture this material are listed in the FDA regulations.

**Typical Applications:-** Metal detectable seals, gaskets, joints and strips used in sensitive food, drink and pharmaceutical applications.

Issue 1

October 2004

Check out the download area of our website [www.j-flex.co.uk](http://www.j-flex.co.uk) for other product information



Clockpress Limited  
Registered in England.  
Registration No. 2448048  
Registered Office:  
St Hugh's, 23 Newport,  
Lincoln LN1 3DN

### J-FLEX RUBBER PRODUCTS

Engineering Rubber Components & Specialised Sheeting Products

Unit 1, London Road Business Park, Retford,  
Nottinghamshire, England DN22 6HG  
tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409  
[www.j-flex.co.uk](http://www.j-flex.co.uk)

