



# Product information

## MICRASIL®

### Antimicrobial Silicone Rubber

<b>MicraSil®</b>	The pro-active Antimicrobial Silicone Rubber from J-Flex, providing protection against contamination from bacterium; fungi & algae.
<b>PROBLEM:</b>	The growth of bacteria, fungi and algae on and around rubber seals, gaskets and sheets – forms a substantial threat in food safety. In addition the growth of microbes on rubber surfaces can lead to foul odours, discolouration and the formation of mildew and slime – leading to surface degradation that will significantly reduce component lifespan.
<b>SOLUTION:</b>	MicraSil® Silicone Rubber which offers microbial protection is a must in the medical, pharmaceutical, food and beverage process industry.
<b>SO HOW DOES IT WORK?</b>	
<ul style="list-style-type: none"> <li>• The bacteria or microbes make contact with the rubber part.</li> <li>• The bacteria absorb the free silver ions on the surface of the rubber.</li> <li>• The silver ions destroy the bacteria / microbes by breaking down their cell walls.</li> <li>• The silver ions inhibit the growth of any micro-organisms and deter it from contaminating or colonising its surface.</li> </ul>	
<b>ADVANTAGES OF MICRASIL®:</b>	
<ul style="list-style-type: none"> <li>• The free silver ions on the outside of the rubber remain active even after several washes.</li> <li>• The silver ions are released in areas that are hard or impossible to access with cleaning detergents ( e.g. hairline cracks in the seal or gasket) – whereby bacterial growth is suppressed.</li> <li>• Reduced downtime, lost production and maintenance costs.</li> <li>• MicraSil® additive has been approved by:- FDA; EPA &amp; EFSA.</li> <li>• Has no taste + no smell + non-toxic + non leaching + non corrosive</li> <li>• Temperature Resistance : Up to 200°C</li> <li>• Independently tested and found to destroy on contact – MRSA, E-coli, Salmonella, Campylobacter, etc.</li> <li>• Independently tested the additive is mixed at the time of manufacture and lasts for the usefulness life of the product. As it is not solely applied to the surface, performance is not affected by scratches; bumps or general wear and tear.</li> <li>• MicraSil® can be supplied as gaskets; sheets; seals; extruded sections – in short anything that can be moulded, extruded or calendered.</li> </ul>	

Issue 1

November 2008

MicraSil® is a Registered Trademark of J-Flex Rubber Products

Check out the download area of our website [www.j-flex.co.uk](http://www.j-flex.co.uk) for other product information



Clockpress Limited  
 Registered in England.  
 Registration No. 2448048  
 Registered Office:  
 St Hugh's, 23 Newpork,  
 Lincoln LN1 3DN

## J-FLEX RUBBER PRODUCTS

Engineering Rubber Components & Specialised Sheeting Products

Unit 1, London Road Business Park, Retford,  
 Nottinghamshire, England DN22 6HG  
 tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409  
[www.j-flex.co.uk](http://www.j-flex.co.uk)



# Product information

## MICRASIL® ANTIMICROBIAL SILICONE RUBBER 60° SHORE 'A'

COLOUR : YELLOW OR BLUE

PROPERTY	TEST METHOD	UNITS	SPECIFICATION LIMITS	TYPICAL VALUE
HARDNESS	ASTM D2240 DIN 53505	°SHORE A	60° (+/-5)	62
TENSILE STRENGTH	BSISO 37 DIN 53505 die S1 ASTM D412 Die C	MPa psi	5.5 min 795 min	10.5 1523
ELONGATION @ BREAK	BSISO 37 ASTM D412 die C DIN 53504 die S1	%	250 min	360
TEAR STRENGTH	BS ISO 34-1 method C ASTM D624 die B	N/mm lb/in	10.0 min 57.0 min	14.7 83.9
COMPRESSION SET 24hrs @ 150°C	BS 903 PT A6 TYPE B DIN 53517 type II	%	30 max	17
22HRS @ 300°F	ASTM D395 method B type 2	%	30 max	15
THERMAL CONDUCTIVITY	VDE 0304		0.24 W.m <sup>-1</sup> .K <sup>-1</sup>	
TEMPERATURE RANGE	-60°C to +230°C (Continuous)		+250°C (Intermittent)	
GENERAL THICKNESSES	0.3, 0.5, 0.8, 1.0, 1.5, 2.0, 3.0, 4.0, 5.0, 6.0, 8.0, 10.0 & 12.0mm (Check with our Sales Office for specific availability)			

These sheetings have been fully post cured and all the ingredients used to produce these sheetings are listed in FDA 21 CFR 177. 2600. We manufacture our FDA materials in accordance with FDA guidelines set out in 21 CFR 177.2600 and the manufactured materials have been tested to, and comply with the tests listed in 21 CFR 177.2600 (d) to (h). This makes them suitable for contact with dry, aqueous and fatty foods defined by the FDA. As stated in 21 CFR 177.2600 it is recommended that the manufactured article is thoroughly cleansed prior to first use in contact with food.

**WRAS APPROVAL NO: 0806508:-**

Approved for cold & hot potable water use up to 85°C in accordance to BS 6920.

ISSUE 1

November 2008

Check out the download area of our website  
[www.j-flex.co.uk](http://www.j-flex.co.uk) for other product information



Clockpress Limited  
Registered in England.  
Registration No. 2448048  
Registered Office:  
St Hugh's, 23 Newport,  
Lincoln LN1 3DN

### J-FLEX RUBBER PRODUCTS

Engineering Rubber Components & Specialised Sheeting Products

Unit 1, London Road Business Park, Retford,  
Nottinghamshire, England DN22 6HG

tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409  
[www.j-flex.co.uk](http://www.j-flex.co.uk)

