



Product information

TRANSLUCENT PLATINUM CURED SILICONE RUBBER SHEETING QUALITY: PLAT. 60



PROPERTY	TEST METHODS	UNIT	TYPICAL VALUE
HARDNESS	DIN 53505	° SHORE A	60° (+/-5°)
TENSILE STRENGTH	DIN 53504	Mpa	11 min
ELONGATION TO FAILURE	DIN 53504	%	450
TEAR STRENGTH	ASTM D 624 B	N/mm	33
COMPRESSION SET	ISO 815	%	25
TEMPERATURE RANGE	-55°C to +200 °C		

Ingredients conform with FDA & BfR listed raw materials.

Issue 3

June 2008

Check out the download area of our website
www.j-flex.co.uk for other product information



Clockpress Limited
 Registered in England.
 Registration No. 2448048
 Registered Office:
 St Hugh's, 23 Newport,
 Lincoln LN1 3DN

J-FLEX RUBBER PRODUCTS

Engineering Rubber Components & Specialised Sheeting Products

Unit 1, London Road Business Park, Retford,
 Nottinghamshire, England DN22 6HG
 tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409
www.j-flex.co.uk

