



# Product information

## SILICONE RUBBER 10° SHORE A



PROPERTY	VALUE
HARDNESS:	10° (+/-5°) Shore 'A'
SPECIFIC GRAVITY:	1.04(+/-0.02) Gr/cm <sup>3</sup>
TENSILE STRENGTH:	3.5 N/mm <sup>2</sup>
ELONGATION @ BREAK:	850%
TEAR STRENGTH:	6 KN/m
TEMPERATURE RANGE:	-60°C to 200°C Continuous +250°C Intermittent

Issue 1

August 2005

Check out the download area of our website  
[www.j-flex.co.uk](http://www.j-flex.co.uk) for other product information



Clockpress Limited  
 Registered in England.  
 Registration No. 2448048  
 Registered Office:  
 St Hugh's, 23 Newport,  
 Lincoln LN1 3DN

### J-FLEX RUBBER PRODUCTS

Engineering Rubber Components & Specialised Sheeting Products

Unit 1, London Road Business Park, Retford,  
 Nottinghamshire, England DN22 6HG  
 tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409  
[www.j-flex.co.uk](http://www.j-flex.co.uk)

