

Product information

FOOD QUALITY TRANSLUCENT SILICONE RUBBER SHEETING 40° SHORE 'A'



PROPERTY	TYPICAL VALUE	NORMS
QUALITY NO:	T040	
HARDNESS:	40° (+/-5°) Shore 'A'	DIN53505
SPECIFIC DENSITY:	1.15(+/-0.05) g/cm ³	DIN53479
TENSILE STRENGTH:	7.0 Mpa (min)	DIN53504
ELONGATION @ BREAK:	400% (min)	DIN53504
COMPRESSION SET: 24hrs @ 150°C	35% (max)	DIN53517
TEAR STRENGTH:	10 N/mm (min)	BS EN 903 pt A2 die C
TEMPERATURE RANGE:	-60°C to 230°C	

This sheeting is produced from FDA Approved raw material under regulation CFR 177. 2600 in the Code of Federal Regulations. The sheeting has been fully post cured as regulated making it fully FDA Compliant and suitable for food processing /contact applications.

WRAS APPROVAL NO: 0806508:-

Approved for cold & hot potable water use up to 85°C in accordance to BS 6920.

Issue 2

July 2008

Check out the download area of our website
www.j-flex.co.uk for other product information



Clockpress Limited
Registered in England.
Registration No. 2448048
Registered Office:
St Hugh's, 23 Newport,
Lincoln LN1 3DN

J-FLEX RUBBER PRODUCTS
Engineering Rubber Components & Specialised Sheeting Products

Unit 1, London Road Business Park, Retford,
Nottinghamshire, England DN22 6HG
tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409
www.j-flex.co.uk

