



# Product information

## VITON® RUBBER / NOMEX INSERTION SHEET 65° SHORE 'A'

Smooth Surface Finish Both Sides

Rolls: 1.0m wide x 10 metres long



Physical Properties of Viton Rubber	
Hardness	65° Shore 'A' (+/-5°)
Tensile Strength	10.0 Mpa
Elongation at Break	325%
Tear Strength	20KN/m
Compression Set:	
@ 100°C for 72hrs	15%
@ 150°C for 72hrs	15%
@ 200°C for 72hrs	25%
Nomex Meta-Aramid Fibre	
Weight	135g/ m <sup>2</sup>
Weave	13 x 13 per cm
Thickness	0.45mm
Tensile Strength	Approximately 15Kg / cm
Adhesion	4.23 Kgf / 25mm

Finished Thickness: 1.5mm (+/-0.40mm); 2mm (+/-0.40); 3mm (+/-0.40mm)

Viton® is the registered trademark of DuPont Performance Elastomers.

Issue 3

December 2007

Check out the download area of our website  
[www.j-flex.co.uk](http://www.j-flex.co.uk) for other product information



Clockpress Limited  
 Registered in England.  
 Registration No. 2448048  
 Registered Office:  
 St Hugh's, 23 Newport,  
 Lincoln LN1 3DN

### J-FLEX RUBBER PRODUCTS

Engineering Rubber Components & Specialised Sheeting Products

Unit 1, London Road Business Park, Retford,  
 Nottinghamshire, England DN22 6HG

tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409  
[www.j-flex.co.uk](http://www.j-flex.co.uk)

