



Product information

RED IRON OXIDE SILICONE REINFORCED WITH 1 PLY GLASS CLOTH INSERTION

BASE FABRIC: GLASS CLOTH		VALUE
Composition	Warp & Weft	Glass
Weight		204g/m ²
Warp Count		680 d'tex
Weft Count		680 d'tex
Weave		Plain
Thickness		0.18mm

COMPOUND CHARACTERISTICS	VALUE
Composition	Silicone Rubber
Colour	Red Iron Oxide
Weight	1.20Kg/m ³
Hardness	60°
Adhesion	>9N/mm
Temperature Range	-60° C to +230° C

Finished Article Characteristics

Specification	Construction (Sil + Glass + Sil)	Thickness	Width
1.5mm	0.65 + 0.2 + 0.65	1.5mm (+/-0.2mm)	1200mm Max
2.0mm	0.9 + 0.2 + 0.9	2.0mm (+/-0.2mm)	1200mm Max
3.0mm	1.4 + 0.2 + 1.4	3.0mm (+/-0.2mm)	1200mm Max
4.0mm	1.9 + 0.2 + 1.9	4.0mm (+/-0.2mm)	1200mm Max

Issue 4

March 2011

Check out the download area of our website
www.j-flex.co.uk for other product information



Certificate No. RS 27920
 Approved to
 BS EN ISO 9001:2000

Clockpress Limited
 Registered in England.
 Registration No. 2448048
 Registered Office:
 St Hugh's, 23 Newport,
 Lincoln LN1 3DN

J-FLEX RUBBER PRODUCTS

Engineering Rubber Components & Specialised Sheeting Products

Unit 1, London Road Business Park, Retford,
 Nottinghamshire, England DN22 6HG

tel: +44 (0) 1777 712400 fax: +44 (0) 1777 712409
www.j-flex.co.uk

